



Aluminium Alloy - 5005 - H34 Sheet

SPECIFICATIONS

Commercial	5005
EN	5005

Aluminium alloy 5005 is a medium strength alloy with very good resistance to atmospheric corrosion and very good weldability that is highly suitable for decorative anodising. PLEASE NOTE THAT WHILST ALLOY 5005 IS SUITABLE FOR ANODISING, STREAKS CAN OCCUR - IF THE FINISH YOU ARE SEEKING IS CRITICAL PLEASE SPECIFY 'SPECIAL ANODISING QUALITY' AT TIME OF ORDER.

Applications - Alloy 5005 is typically used for:
 Buildings – Roofing, Cladding, Corrugated Sheet
 Signage, Road Signs & Name Plates
 Food & Chemical Equipment
 Furniture
 Anodised Parts
 HVAC Equipment
 Packaging
 Pipe and Tube
 Can Bodies

CHEMICAL COMPOSITION

BS EN 573-3:2009 Alloy 5005	
Element	% Present
Magnesium (Mg)	0.5 - 1.1
Iron (Fe)	0.7 max
Silicon (Si)	0.3 max
Zinc (Zn)	0.25 max
Manganese (Mn)	0.2 max
Copper (Cu)	0.2 max
Others (Total)	0.15 max
Chromium (Cr)	0.1 max
Other (Each)	0.05 max
Aluminium (Al)	Balance

ALLOY DESIGNATIONS

TEMPER TYPES

The most common tempers for 5005 aluminium are:

- H34 - Stabilised - A low temperature thermal treatment or heat introduced during manufacture which stabilises the mechanical properties and relieves residual internal stress, plus usually improves ductility

SUPPLIED FORMS

- Sheet

GENERIC PHYSICAL PROPERTIES

Property	Value
Density	2.70 g/cm ³
Melting Point	655 °C
Modulus of Elasticity	69.5 GPa
Thermal Expansion	23.5 x10 ⁻⁶ /K
Thermal Conductivity	201 W/m.K
Electrical Resistivity	52 % IACS
Electrical Resistivity	0.033 x10 ⁻⁶ Ω .m

MECHANICAL PROPERTIES

BS EN 485-2:2008 Aluminium Sheet 0.2mm to 12.5mm	
Property	Value
Proof Stress	110 Min MPa
Tensile Strength	145 - 185 MPa
Hardness Brinell	47 HB

The properties above are for material in the H34 condition



Aluminium Alloy - 5005 - H34 Sheet

CONTACT

Address:	Wilsons Ltd Nordic House Old Great North Road Huntingdon PE28 5XN
Tel:	+44 (0)1480 456421
Email:	sales@wilsonsmetals.com
Web:	www.wilsonsmetals.com

REVISION HISTORY

Datasheet Updated	13 November 2018
-------------------	------------------

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.