



Aluminium Alloy - 5052 - H32 Sheet and Treadplate

SPECIFICATIONS

Commercial	5052
EN	5052

Aluminium alloy 5052 in H32 temper has very good corrosion resistance to seawater and marine and industrial atmosphere. It also has very good weldability and good cold formability. It is a medium to high strength alloy with a strength slightly higher than 5251 and a medium to high fatigue strength.

Properties

Alloy 5052-H32 has a range of useful properties:

Decorative Finish
 Hard Wearing
 Non-Slip
 Corrosion Resistant
 Low Maintenance
 Anti-Static
 Light-weight

Applications

Amongst the applications for Alloy 5052 are:

Treadplate
 Boilermaking
 Containers
 Nameplates
 Road Signs
 Architectural Paneling
 Welded Tubes
 Chemical Industry
 Irrigation
 Desalination units
 Pressure Vessels
 Rivets

CHEMICAL COMPOSITION

BS EN 573-3:2009
 Alloy 5052

Element	% Present
Magnesium (Mg)	2.2 - 2.8
Iron (Fe)	0.4 max
Chromium (Cr)	0.15 - 0.35
Silicon (Si)	0.25 max
Others (Total)	0.15 max
Manganese (Mn)	0.1 max
Copper (Cu)	0.1 max
Zinc (Zn)	0.1 max
Other (Each)	0.05 max
Aluminium (Al)	Balance

ALLOY DESIGNATIONS

Alloy 5052 corresponds to the following standard designations and specifications **but may not be a direct equivalent**:

Al Mg 2.5
 Al 2.5Mg Cr

TEMPER TYPES

The most common tempers for 5052 aluminium are:

- H32 - Work hardened by rolling then stabilised by low-temperature heat treatment to quarter hard

SUPPLIED FORMS

The main form supplied of this alloy is TripleGrip Treadplate

- Sheet
- Extrusions
- Plate
- Treadplate/Patterned Sheet



Aluminium Alloy - 5052 - H32 Sheet and Treadplate

GENERIC PHYSICAL PROPERTIES

Property	Value
Density	2.68 g/cm ³
Melting Point	605 °C
Thermal Expansion	23.7 x10 ⁻⁶ /K
Modulus of Elasticity	70 GPa
Thermal Conductivity	138 W/m.K
Electrical Resistivity	0.0495 x10 ⁻⁶ Ω .m

MECHANICAL PROPERTIES

BS EN 485-2:2008
Sheet and Treadplate
0.2mm to 6.00mm

Property	Value
Proof Stress	130 Min MPa
Tensile Strength	210 - 260 MPa
Hardness Brinell	61 HB

The properties above are for material in the H32 condition

WELDABILITY

Weldability – Gas: Good
Weldability – Arc: Very Good
Weldability – Resistance: Very Good
Brazability: Acceptable
Solderability: Not recommended

FABRICATION

Workability – Cold: Good
Machinability: Acceptable

CONTACT

Address: Wilsons Ltd
Nordic House
Old Great North Road
Huntingdon
PE28 5XN
Tel: +44 (0)1480 456421
Email: sales@wilsonsmetals.com
Web: www.wilsonsmetals.com

REVISION HISTORY

Datasheet Updated 13 November 2018

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.