



Aluminium Alloy - 6106 - T6 Extrusions

SPECIFICATIONS

Commercial	6106
EN	6106

Aluminium alloy 6106 is an extrusion alloy designed to provide optimum combination of mechanical properties, complexity of shape, minimum section thickness and good surface finish together with the good resistance, weldability and formability associated with the 6000 series alloys. Very complex shapes are possible which are not obtainable with stronger alloys such as 6182.

(6000 series alloys achieve their properties by thermal treatment which can be adjusted to provide combinations of strength and formability conditions with good corrosion resistance and weldability. Because the properties are obtained by thermal treatment, fusion welding reduces the non-welded properties by up to 50%.)

Applications

Alloy 6106 is typically used for:

- ~ Structural applications
- ~ Ladders, pylons and towers
- ~ Railway Rolling Stock
- ~ Marine applications
- ~ Automotive structures

CHEMICAL COMPOSITION

BS EN 573-3:2009 Alloy 6106	
Element	% Present
Magnesium (Mg)	0.4 - 0.8
Silicon (Si)	0.3 - 0.6
Iron (Fe)	0.35 max
Copper (Cu)	0.25 max
Manganese (Mn)	0.05 - 0.2
Chromium (Cr)	0.2 max
Others (Total)	0.15 max
Zinc (Zn)	0.1 max
Titanium (Ti)	0.1 max
Other (Each)	0.05 max
Aluminium (Al)	Balance

ALLOY DESIGNATIONS

TEMPER TYPES

The most common temper for 6106 aluminium is:

- T6 - Solution heat treated and artificially aged

SUPPLIED FORMS

- Extrusions

GENERIC PHYSICAL PROPERTIES

Property	Value
Density	2.70 g/cm ³
Melting Point	655 °C
Thermal Expansion	23.4 x10 ⁻⁶ /K
Modulus of Elasticity	69.5 GPa
Thermal Conductivity	192 W/m.K
Electrical Resistivity	0.035 x10 ⁻⁶ Ω .m

MECHANICAL PROPERTIES

BS EN 755-2:2008 Profiles only Up to 10mm Wall Thickness	
Property	Value
Proof Stress	200 Min MPa
Tensile Strength	250 Min MPa
Elongation A50 mm	6 Min %
Hardness Brinell	75 HB
Elongation A	8 Min %

Above readings refer to profiles in the T6 condition only.



Aluminium Alloy - 6106 - T6 Extrusions

WELDABILITY

Weldability – Gas: Good
Weldability – Arc: Very Good
Weldability – Resistance: Good
Brazability: Good
Solderability: Good

FABRICATION

Workability – Cold: Acceptable, but limited in T6 temper
Machinability: Good

CONTACT

Address:	Wilsons Ltd Nordic House Old Great North Road Huntingdon PE28 5XN
Tel:	+44 (0)1480 456421
Email:	sales@wilsonsmetals.com
Web:	www.wilsonsmetals.com

REVISION HISTORY

Datasheet Updated	13 November 2018
-------------------	------------------

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.