



## Aluminium Alloy - L81 H16 or H26 Sheet

### SPECIFICATIONS

Commercial	5251 - Obsolete
------------	-----------------

#### Applications:

Nameplates, traffic (road) signs, architectural paneling. Welded tubes, chemical industry, irrigation. Offshore applications, welded structures. Pressure vessels, boilermaking.

#### Characteristic Properties:

Very good corrosion resistance to seawater and marine and industrial atmosphere. Very good weldability. Medium to high strength alloy for sheet products slightly lower than 5086. Medium high fatigue strength. Good cold formability.

### CHEMICAL COMPOSITION

BS 3L81(1985)  
Alloy L81

Element	% Present
Magnesium (Mg)	1.7 - 2.4
Iron (Fe)	0.5 max
Manganese (Mn)	0.1 - 0.5
Silicon (Si)	0.4 max
Others (Total)	0.15 max
Titanium (Ti)	0.15 max
Chromium (Cr)	0.15 max
Copper (Cu)	0.15 max
Zinc (Zn)	0.15 max
Other (Each)	0.05 max
Aluminium (Al)	Balance

The material shall be supplied cold rolled (H16) or cold rolled and partially annealed (H26).

### ALLOY DESIGNATIONS

Aluminium alloy BS L81 - 5251 is covered by standard BS EN 3L81 (1985)

### TEMPER TYPES

The most common tempers for L81 - 5251 aluminium are:

- H16 - Work hardened by rolling to three-quarter hard, not annealed after rolling
- H26 - Work hardened by rolling then annealed to three-quarter hard

### SUPPLIED FORMS

L81 - 5251 is supplied in the following forms:

- Sheet
- Strip

### GENERIC PHYSICAL PROPERTIES

Property	Value
Density	2.69 g/cm <sup>3</sup>
Melting Point	650 °C
Thermal Expansion	23.6 x10 <sup>-6</sup> /K
Thermal Conductivity	149 W/m.K
Modulus of Elasticity	70.0 GPa
Electrical Resistivity	37.5 % IACS

### MECHANICAL PROPERTIES

BS 3L81(1985)  
Sheet  
0.4mm to 0.8mm

Property	Value
Elongation A50 mm	3 Min %
Tensile Strength	225 Min - 275 Max N/mm <sup>2</sup>
0.2% Proof Stress	175 Min N/mm <sup>2</sup>

Mechanical properties relate to material with a nominal thickness of 0.4mm up to and including 0.8mm. The specification contains other values for different material thicknesses.



## Aluminium Alloy - L81 H16 or H26 Sheet

### CONTACT

Address:	Wilsons Ltd Nordic House Old Great North Road Huntingdon PE28 5XN
Tel:	+44 (0)1480 456421
Email:	<a href="mailto:sales@wilsonsmetals.com">sales@wilsonsmetals.com</a>
Web:	<a href="http://www.wilsonsmetals.com">www.wilsonsmetals.com</a>

### REVISION HISTORY

Datasheet Updated	09 January 2014
-------------------	-----------------

### DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.