

Aluminium Alloy - L97 T351 Plate

SPECIFICATIONS

Commercial	2024 - Obsolete
------------	-----------------

Applications:

High strength fabricated or machined items in aircraft industries, general engineering, machinery, military equipment, truck wheels. Screw machine products. Structural applications. Rivets.

Characteristic Properties:

Heat treatable alloy. Very good machining characteristics. High strength alloy with a strength slightly higher than 2014(A) and 2017A and 2030. High fatigue strength. Suitable for welding only by resistance welding. Corrosion resistance only with cladding or other protection.

CHEMICAL COMPOSITION

BS 2L97(1971)
Alloy L97

Element	% Present
Copper (Cu)	3.8 - 4.9
Magnesium (Mg)	1.2 - 1.8
Manganese (Mn)	0.3 - 0.9
Iron (Fe)	0.5 max
Silicon (Si)	0.5 max
Titanium + Zirconium (Ti+Zr)	0.2 max
Zinc (Zn)	0.2 max
Chromium (Cr)	0.1 max
Nickel (Ni)	0.05 max
Lead (Pb)	0.05 max
Tin (Sn)	0.05 max
Aluminium (Al)	Balance

ALLOY DESIGNATIONS

Aluminium alloy L97 - 2024 is covered by standard BS 2L97 (1971)

TEMPER TYPES

The most common temper for L97 - 2024 aluminium plate is:

- T351 - Solution heat treated then stress relieved by stretching. Equivalent to T4 condition.

SUPPLIED FORMS

L97 - 2024 aluminium is supplied in the following forms:


- Plate

GENERIC PHYSICAL PROPERTIES

Property	Value
Density	2790 g/cm ³
Melting Point	640 °C
Thermal Expansion	23.10 x10 ⁻⁶ /K
Modulus of Elasticity	73000 GPa
Thermal Conductivity	121 W/m.K

MECHANICAL PROPERTIES

Thickness (mm)	Proof Strength (Min)	Tensile Strength (Min)	Elongation % (Min)
Over 6 up to & incl. 12.5	280	430	10
Over 12.5 up to & incl. 25	280	430	10
Over 25 up to & incl. 40	280	420	9
Over 40 up to & incl. 63	270	410	9
Over 63 up to & incl. 90	270	410	8
Over 90 up to & incl. 115	270	400	8
Over 115 up to & incl. 140	260	390	7



Aluminium Alloy - L97 T351 Plate

CONTACT

Address:	Wilsons Ltd Nordic House Old Great North Road Huntingdon PE28 5XN
Tel:	+44 (0)1480 456421
Email:	sales@wilsonsmetals.com
Web:	www.wilsonsmetals.com

REVISION HISTORY

Datasheet Updated	09 January 2014
-------------------	-----------------

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.