



## Aluminium Alloy - QQ-A-250/5 'O' Sheet

### SPECIFICATIONS

Commercial	2024 Clad
------------	-----------

A medium to high strength alloy with, dependent upon temper, minimum Proof Stress up to 56 ksi / 385 Mpa and minimum Tensile Strength up to 64 ksi / 440 MPa

### CHEMICAL COMPOSITION

SAE AMS QQ A 250/5  
Alloy QQ a 250/5

Element	% Present
Copper (Cu)	3.8 - 4.9
Magnesium (Mg)	1.2 - 1.8
Manganese (Mn)	0.3 - 0.9
Silicon (Si)	0.5 max
Iron (Fe)	0.5 max
Zinc (Zn)	0.25 max
Titanium + Zirconium (Ti+Zr)	0.2 max
Titanium (Ti)	0.15 max
Others (Total)	0.15 max
Chromium (Cr)	0.1 max
Other (Each)	0.05 max
Aluminium (Al)	Balance

### ALLOY DESIGNATIONS

Aluminium alloy QQ-A-250/5 has similarities to the following standard designations and specifications **but may not be a direct comparison:**

Alloy 2024, UNS A92024, AMS 4040, AMS 4041, AMS 4194, AMS 4195, AMS 4274

### TEMPER TYPES

Alloy QQ-A-250/5 is supplied in a wide range of tempers:

- O - Soft
- T3 - Solution heat treated, cold worked and naturally aged
- T361 - Solution heat treated then stress relieved by stretching.
- T4 - Solution heat treated and naturally aged to a substantially stable condition
- T42 - Solution heat treated and naturally aged to a substantially stable condition
- T81 - Solution heat treated, cold worked then artificially aged
- T851 - Solution heat treated then stress relieved by stretching then artificially aged.
- T861

### SUPPLIED FORMS

Alloy QQ-A-250/5 is supplied in CLAD plate and sheet

- Plate
- Sheet

### GENERIC PHYSICAL PROPERTIES

Property	Value
Density	2.74 g/cm <sup>3</sup>
Melting Point	640 °C
Thermal Expansion	23.1 x10 <sup>-6</sup> /K
Modulus of Elasticity	73 GPa
Thermal Conductivity	193 W/m.K
Electrical Resistivity	50.5 % IACS

### MECHANICAL PROPERTIES

Mechanical Properties shown are for 'O' temper

Thickness (mm)	Proof Strength (Min)	Tensile Strength (Min)	Elongation % (Min)
Over 0.2 up to & incl. 1.5	97	207	12
Over 1.6 up to & incl. 12.6	97	221	12



## Aluminium Alloy - QQ-A-250/5 '0' Sheet

### CONTACT

Address:	Wilsons Ltd Nordic House Old Great North Road Huntingdon PE28 5XN
Tel:	+44 (0)1480 456421
Email:	<a href="mailto:sales@wilsonsmetals.com">sales@wilsonsmetals.com</a>
Web:	<a href="http://www.wilsonsmetals.com">www.wilsonsmetals.com</a>

### REVISION HISTORY

Datasheet Updated	18 December 2013
-------------------	------------------

### DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.